

Injection Moulding Processing Guide for Chemieprene TPE PO series**Processing Temperature**

| Temperatures | VALUE(Metic) |
|---------------------|---------------------|
| 1st Zone-Rear | 155-165 °C |
| 2nd Zone-Center | 160-175 °C |
| 3rd Zone-Front | 170-180 °C |
| 4th Zone-Nozzle | 165-175 °C |
| Mold Temperature | 40-50 °C |

Pressure, Velocity, Recovery, Timers

| Pressure | VALUE(Metic) |
|-----------------|----------------------------|
| 1st Stage-Boost | 50-100 kg/ cm ² |
| 2nd Stage-Hold | 25-50 % of Boost |
| Back Pressure | 5-10 kg/ cm ² |

Velocity

| | |
|--------------------|---------------------|
| Injection Velocity | Medium 20-60 mm/sec |
|--------------------|---------------------|

Recovery

| | |
|-------------|------------|
| Screw Speed | 75-125 RPM |
|-------------|------------|

Timers

| | |
|-----------------------|----------|
| Hold Time(Thick part) | 4-10 sec |
| Hold Time(Thin part) | 1-3 sec |

Drying

| | |
|--------------------|---------|
| Drying Temperature | 50-60°C |
| Drying Time | 2-3 hrs |

Purging

Purge thoroughly before and after use of this product with a low flow (0.5-3 MFR) polypropylene(PP) or polyethylene(PE)

Coloring

Color concentrates with polypropylene (PP), ethylene Vinyl acetate (EVA), or low density polyethylene (LDPE) Carries are most suitable for coloring, concentrates based on PVC should not be used. The final determination of color concentrate be determined by the customer.

Regrind

Regrind levels up to 20% can be used with minimal property loss, provided that the regrind is free of contamination.

CP Chemie Resources (Malaysia) Sdn Bhd

URL: www.cpchemie.com

Email: info@cpchemie.com

All Information supplied by or on behalf of CP Chemie Resources (M) Sdn Bhd in relationship to its product, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but the Company assume no liability whatsoever in respect of application, processing or use made of the aforementioned information and products, or any consequence thereof. This data provided shall not absolve the customer of the responsibility to make test for his intended purpose or process. Therefore, the Company makes no warranties and assumes no liability in connection with any use of this data.